

✓ ✓
Page 5, line 16, before "adhesion" insert --an--.

✓ ✓
Page 6, line 1, change "Patent Claims" to read --WE CLAIM:--.

IN THE CLAIMS:

5 Claim 1, line 2, change "characterized by" to read --the method comprising--.

✓ ✓
Claim 2, line 1, change "characterized in that" to read --wherein--.

✓ ✓
Claim 3, line 1, change "1 or 2, characterized in that" to read --2, wherein--.

Please cancel claims 4-7, without prejudice, and substitute the following claims:

10 --10. A method according to claim 2, wherein the step of applying is selected from a group consisting of spraying, brushing and immersing.--

--11. A method according to claim 2, wherein the component part is composed of an alloy selected from the group consisting of nickel-based alloys and cobalt-based alloys.--

15 --12. A method according to claim 2, wherein the drying is implemented for a period of 0.5 to 4 hours.--

at
cont

--13. A method according to claim 2, which includes, prior to the step of alitizing, heat treating the slip layer in argon at a temperature of between 750°C to 1200°C.--

--14. A method according to claim 13, wherein the step of heat treating is for 1 to 6 hours.--

--15. A method according to claim 2, which includes, prior to the step of alitizing, heat treating the slip layer in a vacuum at a temperature range of 750°C to 1200°C.--

Claim 8, line 1, change "~~is~~ characterized in that" to read --15, wherein--.

Please cancel claim 9, without prejudice, and substitute the following claims:

--16. A method according to claim 2, wherein the step of alitizing is implemented at a temperature between 800°C and 1200°C for a duration of 1 to 12 hours.--

--17. A method according to claim 1, wherein the powder is present with a grain size distribution of 5µm through 120µm.--

--18. A method according to claim 1, wherein the step of applying is selected from a group consisting of spraying, brushing and immersing.--

a7
cont

--19. A method according to claim 1, wherein the component part is composed of an alloy selected from a group consisting of nickel-based alloys and cobalt-based alloys.--

5

--20. A method according to claim 1, wherein the step of drying is implemented over 0.5 to 4 hours.--

Sub 9

--21. A method according to claim 1, which includes, prior to the step of alitizing, heat treating the slip layer at a temperature range of 750°C to 1200°C in an atmosphere selected from argon and a vacuum.--

10

--22. A method according to claim 21, wherein the heat treating is implemented for a period of 1 to 6 hours.--

--23. A method according to claim 21, wherein the step of alitizing is implemented at a temperature range of 800°C through 1200°C for a duration of 1 to 12 hours.--

15

--24. A method according to claim 1, wherein the step of alitizing is at a temperature of 800°C through 1200°C for a duration of 1 to 12 hours.--

REMARKS

Claims 1-3, 8 and 10-24 are presented for examination.